

TRADE NAME:	Fiberlogy BVOH
MANUFACTURER:	Fiberlab S.A., Brzezie 387, 32-014 Brzezie, Poland
DESCRIPTION:	BVOH filament designed for printing in FFF/FDM technology, available in natural color, wound on a spool, vacuum-packed in a plastic bag, placed in a cardboard box.

TECHNICAL INFORMATION:

Diameter:	1.75 mm
Diameter Tolerance:	+/- 0.02 mm
Avg Roundness:	+ 0.01 mm
Net Weight:	0.5 kg
Print Temperature:	190°C - 220°C
Bed Temperature:	50°C - 70°C



Physical Properties	Test Method	Unit	Typical Value
Specific Density	ISO 1183	g/cm ³	1.14
Mechanical Properties	Test Method	Unit	Typical Value
Tensile Strength @ Break	ISO 527	MPa	45
Elongation @ Break	ISO 527	%	9
Flexural Strength	ISO 178	MPa	71
Flexural Modulus	ISO 178	MPa	2900
Thermal Properties	Test Method	Unit	Typical Value
Heat Distortion Temperature @ 0.45 MPa	ISO 75	°C	-
Heat Distortion Temperature @ 1.8 MPa	ISO 75	°C	-
Vicat Softening Temperature	ISO 306	°C	92
Glass Transition Temperature T _g	DSC	°C	68
Melting Temperature T _m	DSC	°C	175
Continuous Use Temperature (UL Yellow Card)	UL 746	°C	-

The information set forth herein has been gathered from standard reference materials and/or supplier test data. To the best knowledge and belief of Fiberlab S.A. they are accurate and reliable. Information is offered only for your consideration, investigation and verification. Fiberlab S.A. makes no warranties, expressed or implied, with respect to the use of such information or the use of the specific material identified herein combination with any other material or process, and assumes no responsibility therefore.

Last update: January 21, 2022